



RAMSAUER®
DICHTSTOFFE

1035 SILIKON

BLOCKPROFIL

(Silicone Block Profile)

TECHNICAL DATA

Shore-A-hardness: 70
Tensile strength DIN 53504: 9 – 13 N/mm²
Elongation at break DIN 53504: 300 – 500 %
Density DIN 53479: 1.16 – 1.25 g/cm³
Rebound resilience DIN 53512: 40 – 60 %
Compression set DIN 53517: 0 – 50 %
Packaging: Rolls of 10 lineal metres

CHARACTERISTICS

Block profile of highly viscous silicone rubber with an adhesive coat on one side for convenient installation. Silicone block profiles by Ramsauer are highly UV-resistant, weather-resistant and colour-fast.



APPLICATION

Silicone block profiles by Ramsauer are particularly suitable for use as spacers in glazing and metal frames (preventing the loss of heat), and as a glazing support for flat roofs.

THERMAL CHARACTERISTICS

The silicone block profiles have high elasticity under permanent load at temperatures of approx. -60°C to +200°C.

DIMENSIONS

Thickness x Width	Lineal metres per roll	Lineal metres per carton
3.2 x 9 mm	10 lin.m	180 lin.m
4.8 x 9 mm	10 lin.m	190 lin.m

HAZARD ADVICE

The product is not a hazardous substance within the meaning of the German Hazardous Substances Ordinance ("Gefahrstoffverordnung"). For further information refer to the Safety Data Sheet.

SAFETY ADVICE, INSTRUCTIONS FOR DISPOSAL

Consult the current EC Safety Data Sheet which is available at any time on our website at www.ramsauer.at.

LIABILITY FOR DEFECTS

The information provided including but not limited to the proposals for processing and using our products is based on our knowledge and experience, usually at the time of going into print. The results of work may deviate from this information depending on the specific circumstances, in particular with respect to substrates, processing and environmental conditions. Therefore, neither this information nor any oral counselling shall constitute warranty or give rise to any liability on whatever legal ground for any specific result of work, unless we acted intentionally or by gross negligence.

Ramsauer warrants that its products will have the technical characteristics according to the Technical Data Sheets up to their expiry date.

Product users must consult the latest data sheet which is available upon request. Our current General Terms and Conditions apply which are available for download on our website www.ramsauer.at.



QUALITY YOU CAN RELY ON

Ramsauer GmbH & Co KG, 4822 Bad Goisern/Hallstätter See, Sarstein 17, Austria

Phone: +43 (0)6135 8205-0, Fax: +43 (0)6135 8323 - Email: office@ramsauer.at - Internet: www.ramsauer.at