




RAMSAUER®

395

LASTING BONDS.

Dach Dicht

1-component hybrid sealant



Technical data sheet

Version: 04-2023

Tests:

- Fulfils the French VOC requirement Class A+



1. Mechanical Properties

Basis	Hybrid MS polymer sealant
Skin formation time	~ 15 Min. (23°C/50% relative humidity)
Full curing time	~2.0 mm/24 hours (at +23°C/50% relative humidity)
Density	~ 1.53 (EN ISO 1183-1)
Shore A hardness	~ 40 (DIN EN ISO 868)
Volume shrinkage	~ 2.5% (EN ISO 10563)
Tear propagation resistance	~ 13.1 N/mm (ISO 34-1)
Tensile stress at break	~ 1.0 N/mm ² (DIN EN ISO 8339)
Module	~ 0.81 N/mm ² (DIN EN ISO 8339)
Elongation at break	~ 200% (DIN EN ISO 8339)
Resistance to high and low temperatures	-40°C to +100°C (up to +120°C short-term)
Application temperature (substrate, environment)	Lower + 5°C, upper + 35°C
Admissible total deformation	25%
Colours	Signal grey RAL7004, anthracite
Packaging	310 ml cartridge, other containers on request
Shelf life of cartridges and foil bags	12 months in original packaging in cool and dry storage conditions

2. Properties

Silicone-free hybrid sealant. Excellent adhesion on most substrates occurring in the roof area. Our 395 Dach Dicht has no corrosive properties. Excellent UV, weathering and aging resistance. The material can also be used on damp substrates. Due to the high elongation at break value, the product can absorb high mechanical loads, e.g. due to linear expansions, etc., very well.



RAMSAUER®

395

LASTING BONDS.

Dach Dicht

3. Priming table

Key

+	Good adhesion without priming
-	No adhesion
Primer	Recommended primer

Glass	+
Tiles	+
Pine wood	+
Wet ground concrete	+
Concrete, formwork smoothness	+
Steel DC 04	+
Hot-dip galvanised steel	+
Stainless steel	+
Zinc	+
Aluminium	+
Aluminium AlMg1	+
Aluminium AlCuMg1	+
Aluminium 6016	+
Anodised aluminium	+
Brass MS 63 Hardness F 37	+
PVC Kömadur ES	+
PVC soft	+
PC Makrolon Makroform 099	+
Polyacrylic PMMA XT 20070 Röhm*1	Primer 40
Polystyrene PS Iroplast	+
ABS Metzoplast ABS 7 H	Primer 100
PET	+
PU waste quality	+
Copper	+
Polycarbonate	+
PMMA Röhm sanitary quality	Primer 100
Mirrors*2	-
Natural stone	-

This table is based on adhesion tests with Rocholl test specimens under laboratory conditions. In practice, the adhesive properties depend on a large number of external influences (weathering, contamination, loads, etc.). Therefore, this table is for guidance only and does not constitute a binding statement. For further information please contact our application engineering department. The tests carried out above only refer to the adhesive properties and have no significance in terms of compatibility with the stated substrates.

*1: Different PLEXIGLAS® types exhibit certain differences in their chemical resistance. Stresses must be expected in some applications. The resulting stresses, in combination with certain agents, can lead to "stress cracking". The duration, temperature and concentration of the acting substance have a fundamental influence on any "stress cracks". When using our products in combination with PLEXIGLAS®, the suitability must therefore be checked in advance.

*2: The compatibility with various mirror coatings by different manufacturers is regularly tested in our laboratory. Advance testing is recommended due to production processes of the various manufacturers, into which we have no insights, and as a function of the existing substrate and bonding variants.

4. Application

395 Dach Dicht has been specially developed for use in waterproofing roofs. Due to its excellent adhesion to metallic substrates and concrete, the compound can also be used for perimeter joints. The material is characterised by good adhesion to EPDM sheets. Due to the wide variety of EPDM films, however, we recommend that you carry out your own adhesion and compatibility tests. Not approved for waterproofing/bonding roofing membranes/foils. Please contact our application engineering department for further information.



RAMSAUER®

395

LASTING
BONDS.

Dach Dicht

5. Meets the requirements of IVD instruction sheet

No. 19-1	Sealing of joints and connections in the roof area. Possible applications of sprayable sealants, assembly adhesives, butyl sealing tapes and profiles.
No. 25	Sealing joints and connections in plumbing
No. 31	Refurbishment of joint seals in building construction
No. 35	Sealing and bonding in construction - Systems - Classification - Application

6. Processing

General instructions: The expiry date of the material must be observed, otherwise the stated mechanical properties of the product can no longer be guaranteed. Observe the ambient temperature and substrate temperature. When processing during the summer months, the substrate temperature of the substrates to be sealed/adhesion bonded must be observed. Temperatures above +35 °C during processing can negatively influence the material properties. Before applying, it must be ensured that all building materials in the contact area are compatible with the sealant.

Pre-treatment of the adhesion surfaces: the adhesion surfaces must be load-bearing, dry, and free of dust, grease, and oil. If required, carefully pre-treat the adhesion surfaces using a suitable primer. For adhesion bonding of water vapour impermeable substrates, it is recommended that the sealant be moistened. **Joint design:** For motion compensating joints, the dimensions must be designed to absorb the maximum motion expected. The joint cross-section must be planned in advance and adhered to. Joint dimensions that do not comply with the state of the art are impermissible. **Applying the sealant:** The product can be applied with any commercially available cartridge gun. Working within the application temperature limits, the product must be applied uniformly to the joint avoiding inclusions. If the substrate is pretreated with primer, its flash-off time must be observed. When reworking, good contact with the adhesive surfaces/joint edges must be ensured (using Ramsauer tooling agent). The joint must be tooled within the skin formation time. **Rework:** Any contamination caused by the use of tooling agents must be removed and cleaned up immediately. Contamination from adjacent substrates must be cleaned up when fresh, this is also recommended for contaminated processing equipment.

7. Application restrictions

Caution: The product is not suitable for underwater joints in swimming baths and aquariums. Not suitable for sealing and bonding natural stone (edge zone contamination). For use in conjunction with roofing membranes/foils, please contact our application engineering department. Not approved for bonding mirror elements and/or coated glazing units - independent series of tests are recommended for this application. High-modulus sealants are not suitable for on-site substrates with low inherent strength, e.g., renders, aerated concrete, ETICS, etc.). When coating the sealing compound with alkyd resin paints, incompatibilities may occur (curing problems, sticky surfaces, discolourations, etc.). As a general rule, if the hybrid compound is coated subsequently, its compatibility with the coating or paint system used must be checked. Not suitable for sealing glass rebates. Avoid touch contact with materials containing bitumen and plasticizers, e.g. butyl, neoprene, insulating paints or bituminous coating, etc. Environmental influences (e.g., high temperature, UV exposure, chemical influences such as vapours, etc.) can affect the colours, but this has no negative effect on the mechanical properties. In case of bonded joints exposed to UV, or for sealing glass, please contact our application engineering department. Before applying, the user must ascertain that the building materials (solid, liquid or in gaseous form) are compatible with the sealant in the contact area. High substrate or base temperatures during processing can lead to impairments of the mechanical properties.

8. Safety instructions

Please refer to the current EC safety data sheets. Data sheets are available at any time from our website at www.ramsauer.eu.



RAMSAUER®

**LASTING
BONDS.**

395

Dach Dicht

9. Application notes

Good ventilation must be ensured during processing and curing. Due to the large number of possible influences during processing and application, the processor must always carry out a test processing before use. Note the expiry date of the material. 1-component sealants are not suitable for full-surface bonding. The curing speed increases with increasing coating thickness. If the 1-component material is used in coating thicknesses of more than 15 mm, please contact our application engineering department. If the products are stored and/or transported over a longer period of time (several weeks) at higher temperatures/humidity, the shelf life may be reduced or the material properties may change.

10. Liability for defects

The information, in particular the suggestions for the processing and use of our products, is based on our knowledge and experience in normal use cases at the time of printing. Depending on the specific circumstances, in particular with regard to substrates, processing and environmental conditions, the results may differ from this information. Therefore the guarantee of a work result or a liability, for whatever legal reasons, can be justified neither from these references, nor from a verbal consultation, unless we are guilty of intent or gross negligence in this respect. Ramsauer guarantees that its products comply with the technical properties specified in the technical data sheets until the expiry date.

Product users must consult the latest technical data sheet, which can be requested from us. Our current General Terms and Conditions apply, which you can download at any time from our homepage at www.ramsauer.eu. On publication of a new version/revision of the technical data sheet, all previous versions of the respective product lose their validity.